

## Product datasheet

Property*	Basis Weight	SCT CD	Burst	Moisture
Method	ISO 536	ISO 9895	ISO 2758	DIN EN 20287
Unit	g/m <sup>2</sup>	kN/m	kPa	%
Variation	+/- 3%	-10%	-10%	+/- 1pt
	90	1,57	212	8
	95	1,64	226	8
	100	1,73	239	8
	105	1,82	251	8
	110	1,91	264	8
	115	1,98	277	8
	120	2,08	290	8
	125	2,16	303	8
	130	2,23	316	8
	135	2,31	327	8
	140	2,40	340	8
	145	2,47	352	8
	150	2,56	365	8
	155	2,66	377	8
	160	2,76	389	8
	165	2,80	402	8
	170	2,89	413	8

\*Values subject to production variation

### Available from Q1 2023

#### Norske Skog Bruck production

- PM3 – 5300 mm
- Capacity: 210.000 tons containerboard
- Basis weights: 90 – 175 g/m<sup>2</sup>
- Reel width: 800 – 2850 mm
- Reel diameter: 1450 mm

### Available from Q1 2025

#### Norske Skog Golbey production

- PM1 – 8700 mm
- Capacity: 550.000 tons containerboard
- Basis weights: 90 – 135 g/m<sup>2</sup>
- Reel width: 500 – 3350 mm
- Reel diameter: 1400 mm

[www.norskeskog.com](http://www.norskeskog.com)

September 2024

