

Product datasheet

Property*	Basis Weight	SCT CD	Burst	Moisture
Method	ISO 536	ISO 9895	ISO 2758	DIN EN 20287
Unit	g/m ²	kN/m	kPa	%
Variation	+/- 3%	-10%	-10%	+/- 1pt
	80	1.40	188	8
	85	1.48	201	8
	90	1.57	212	8
	95	1.64	226	8
	100	1.73	239	8
	105	1.82	251	8
	110	1.91	264	8
	115	1.98	277	8
	120	2.08	290	8
	125	2.16	303	8
	130	2.23	316	8
	135	2.31	327	8
	140	2.40	340	8
	145	2.47	352	8
	150	2.56	365	8
	155	2.66	377	8
	160	2.76	389	8
	165	2.80	402	8
	170	2.89	413	8
	190	3.05	425	8
	200	3.15	432	8
	210	3.25	435	8

*Values subject to production variation

Norske Skog Bruck production ·

- PM3 – 5,300 mm
- Capacity: 210,000 tons containerboard
- Basis weights: 90 – 210 g/m²
- Reel width: 700 – 2,850 mm
- Reel diameter: 1,400 mm

Norske Skog Golbey production ·

- PM1 – 8,700 mm
- Capacity: 550,000 tons containerboard
- Basis weights: 80 – 135 g/m²
- Reel width: 500 – 3,350 mm
- Reel diameter: 1,400 mm

